

## SAW Wires C-Mn and low-alloy steels

OE-SD3 is a coppered SAW wire for welding unalloyed steel grades. The wire is especially designed to be used in multi-run applications with OP 121TT to obtain high chapy toughness values even down to -60°C.

When OE-SD3 is combined with OP 41TTW the weld metal will keep its strength properties even after a very long PWHT (e.g. 16 hrs at 620 °C).

Classification				
EN ISO	14171-A-S3Si			
AWS	A5.17: EH 12K			

## **Chemical analysis (Typical values in %)**

С	Mn	Si	Р	S
0.1	1.7	0.3	≤0.015	≤0.015

## **Packaging data**

Packaging Type Diam(mm) / weight(kg)	B450 25	B570 90	DRUM 300
2.0	•		
2.4	•		•
3.2	•		•
4.0	•	•	•

