



# P 45S

SMAW - (Stick) - MMA  
Un-alloyed


Date: 2021-07-07  
Revision: 22

### Description:

P 45S is a multi-purpose rutile-cellulosic coated electrode suitable for a wide application range in mild steel. The electrode is fully positional, including vertical down and welds with a crisp, steady arc to produce a smooth bead surface with good slag detachability. It is relatively insensitive to rust, dirt and surface coatings. Together with its ability to bridge gaps, the general versatility of P 45S makes it ideal for both shop and site fabrication.

### Applications:

### Welding positions:



### Coating type:

Rutile-cellulosic

### Welding current:

DC+/-, AC OCV ≥ 50 V

For root passes: DC-

### Metal recovery:

90%

### Redrying temperature:

90 °C, 2h

### Chemical composition, wt. %

|         | C    | Si   | Mn   | P     | S     | Cr  | Ni  |
|---------|------|------|------|-------|-------|-----|-----|
| Min     |      | 0,30 | 0,30 |       |       |     |     |
| Typical | 0,07 | 0,4  | 0,5  | 0,015 | 0,015 |     |     |
| Max     | 0,10 | 0,70 | 0,75 | 0,030 | 0,020 | 0,1 | 0,2 |

|         | Mo  | Cu  | V    | Nb   |
|---------|-----|-----|------|------|
| Min     |     |     |      |      |
| Typical |     |     |      |      |
| Max     | 0,1 | 0,2 | 0,05 | 0,05 |

### Mechanical properties

|                       | <u>Specified</u> | <u>Typical</u> |
|-----------------------|------------------|----------------|
| Yield strength, Re:   | ≥420 MPa         | 470 MPa        |
| Tensile Strength, Rm: | 500-560 MPa      | 550 MPa        |
| Elongation, A5        | ≥ 22%            | 24%            |
| Impact energy, CV:    | 0 °C • ≥ 47 J    | 0 °C • 50 J    |

### Classification:

EN ISO 2560-A E 42 0 RC 11  
AWS A5.1 E 6013

### Approvals:

CE  
BV 2Y  
LR 2Ym  
MRS 2  
ABS 2  
DNV 2Y

### Product data:

| Diam.mm | Length mm | Current A | Voltage V | Kg weld metal/<br>kg electrodes | No. of electrodes/<br>kg weld metal | Kg weld metal/<br>hour arc time | Burn-off time/<br>electrode (sec.) |
|---------|-----------|-----------|-----------|---------------------------------|-------------------------------------|---------------------------------|------------------------------------|
| 2,0     | 300       | 40-80     | 24        | 0,7                             | 139                                 | 0,4                             | 40                                 |
| 2,5     | 350       | 70-100    | 25        | 0,7                             | 78                                  | 0,8                             | 48                                 |
| 3,2     | 350       | 90-145    | 25        | 0,7                             | 48                                  | 1,2                             | 49                                 |
| 4,0     | 350       | 120-195   | 25        | 0,7                             | 33                                  | 1,7                             | 58                                 |
| 5,0     | 450       | 180-270   | 26        | 0,75                            | 21                                  | 2,3                             | 64                                 |

\*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and ITW Welding AB expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the corresponding EN ISO specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by ITW Welding AB.

ITW Welding reserves the right to change specifications or approvals without prior notice.