

Technical Data

Jotamastic 87



Product description

Jotamastic 87 is a two-pack surface tolerant, abrasion resistant, high solids polyamine cured epoxy mastic coating which may be applied in high film thickness. Available with different hardeners for varying substrate temperatures, Standard (Std) and Wintergrade (WG). This product is a part of a complete system which is certified not to spread surface flames.

Recommended use

Steel where blast cleaning may not be possible and on hydrojetted surfaces still being moist where gloss retention is of minor importance. Can be used alone or in combination with various systems of primers and topcoats. Gives excellent corrosion protection both in salt and fresh water. If exposed to sunlight chalking may occur.

For application in water ballast tanks at newbuilding stage in accordance with PSPC (IMO Res. MSC 82/W), see the "Application procedure for water ballast tanks - Jotamastic 87".

Film thickness and spreading rate

Standard comp. B	Minimum	Maximum	Typical
Film thickness, dry mils (µm)	6,0(150)	12,0(300)	8,0(200)
Film thickness, wet mils (µm)	7,2(180)	14,6(365)	9,8(245)
Theoretical spreading rate ft ² /gl (m ² /l)	221(5,5)	108(2,7)	164(4,1)
Cold climate comp. B	Minimum	Maximum	Typical
Film thickness, dry mils (µm)	6,0(150)	10,0(250)	8,0(200)
Film thickness, wet mils (µm)	8,0(200)	13,6(340)	10,8(270)
Theoretical spreading rate ft ² /gl (m ² /l)	196(4,9)	120(3)	148(3,7)

Approvals

APAS approved to specification 0156/2, 2973, 2973F, 2976 and 2977.
B1 classification by Det Norske Veritas (DNV) for water ballast tanks.

Physical properties

Color	Limited number
Solids (vol %)*	82 ± 2 Standard comp. B 74 ± 2 Cold climate comp. B
Flash point	Standard hardener: 95°F ± 4 (35°C ± 2) (Setaflash) Cold Climate hardener: 88°F ± 4 (31°C ± 2) (Setaflash)
VOC	1,8 lbs/gal (216 gms./ltr.) USA-EPA Method 24 150 gms/ltr UK-PG6/23(97). Appendix 3 2,1 lbs/gal (250 gms./ltr.) USA-EPA Method 24 210 gms/ltr UK-PG6/23(97). Appendix 3
Gloss	Semigloss
Gloss retention	Fair
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Good
Chemical resistance	Very good
Flexibility	Good

*Measured according to ISO 3233:1998 (E)

Hong Kong rules:

Category of paints - Other vessel coatings; VOC 270 gms/ltr HK EPD method (Ready to use); Exempt compound - N/A; Specific gravity: 1.43 (A+B); Both VOC and Specific gravity values provided are typical values, subject to changes when different colour involved.

Surface preparation

All surfaces should be clean and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Bare steel

Cleanliness: Power tool cleaning to min. SSPC-SP2 "Hand Tool Clean" or St 2, mill scale free (ISO 8501-1:2007). Improved surface treatment (blast cleaning to SSPC-SP10 "Near White Blast" or Sa 2½) will improve the performance. In case of waterjetting the flash rust degree shall not exceed (M) moderate in SSPC and NACE standards for waterjetted surfaces.

Shopprimed steel

Clean, dry and undamaged approved shopprimer.

Coated surfaces

Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information. For maintenance UHPWJ to WJ2 (NACE No.5/SSPC-SP 12) or Power tool cleaning to min. SSPC-SP2 "Hand Tool Clean" or St 2 for rusted areas

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 50°F (10°C) (Std), 23°F (-5°C) in CC and at least 5°F (3°C) above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure proper drying.

Hydrojetting of steel surface makes a wet surface. The surrounding air must have a relative humidity not exceeding 85 %. Before painting the surface shall not be glossy with moisture, but can have a patchy appearance.

Application methods

Spray	Use airless spray
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller	May be used for small areas but not recommended for first primer coat, however when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Application data

Mixing ratio (volume)	Standard hardener: 6 parts Comp. A (base) to be mixed thoroughly with 1 part Jotamastic 87, Std Comp. B (curing agent). Cold Climate hardener: 4 parts Comp. A (base) to be mixed thoroughly with 1 part Jotamastic 87, WG Comp. B (curing agent).
Induction time	10 minutes.
Pot life 73°F (23°C)	Standard hardener: 2 hours Cold climate hardener: 1 hour
Thinner/Cleaner	Jotun Thinner No. 17
Guiding data airless spray	
Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi).
Nozzle tip	0.58-0.79 mm (0.023-0.031")
Spray angle	40-80°
Filter	Check to ensure that filters are clean.
Note	*The temperature of the mixture of base and curing agent is recommended to be at least 59°F (15°C), otherwise extra solvent may be required to obtain correct viscosity. *Too much solvents results in lower sag resistance and slower cure. *If extra solvent is necessary, this should be added after mixing of the two components.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Standard comp. B

Substrate temperature	50°F(10°C)	73°F(23°C)	104°F(40°C)
Surface dry	18 h	7 h	2 h
Through dry	24 h	10 h	4 h
Cured	14 d	7 d	2 d
Dry to recoat, minimum	24 h	10 h	4 h
Dry to recoat, maximum ¹	-	-	-

WG Comp. B

Substrate temperature	23°F(-5°C)	32°F(0°C)	41°F(5°C)	50°F(10°C)	73°F(23°C)
Surface dry	24 h	18 h	12 h	6 h	3.5 h
Through dry	80 h	44 h	26 h	16 h	6 h
Cured	21 d	14 d	7 d	3 d	2 d
Dry to recoat, minimum	80 h	44 h	26 h	16 h	6 h
Dry to recoat, maximum ¹	-	-	-	-	-

1. Provided the surface is free from chalking and other contamination prior to application, there is normally no overcoating time limit. Best intercoat adhesion occurs, however, when the subsequent coat is applied before preceding coat has cured. If the coating has been exposed to direct sunlight for some time, special attention must be paid to surface cleaning and mattening/removal of the surface layer in order to obtain good adhesion.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotamastic 87	2 x 8 mils (200 µm)	(Dry Film Thickness)
Hardtop XP	1 x 2 mils (50 µm)	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

18.7 liter unit: 16 liters (4.23 gallons) Comp. A (base) in a 20 liter container and 2.7 liters (0.71 gallons) Jotamastic 87, Std Comp. B in a 3 liter container.

20 liter unit: 16 liters (4.23 gallons) Comp. A (base) in a 20 liter container and 4 liters (1.05 gallons) Jotamastic 87, WG Comp. B in a 5 liter container.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 4 JANUARY 2012 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED